

Test Report No.: **168481325a 001**

Page 1 of 18

Client: Yiwu Saikun impot and Expotr Co. Ltd
Contact Information: Nd Floor No 77.longxing Road.choujiang street.Yiwu city.zhejiang province
Identification/ Model No(s): Crystal Glass Tea Infuser Bottles
CGTIB-01 to 05
Sample obtaining method: Sending by customer
Condition at delivery: Test item complete and undamaged.
Sample Receiving date: 2024-04-22, 2024-05-29
Testing Period: 2024-05-07 to 2024-06-13
Place of testing: Chemical laboratory Shenzhen

Test Specification:

Test result:

Performed parameter(s) for the compliance with the following regulations concerning materials in contact with foodstuff:

- Regulation (EC) No 1935/2004

PASS

Other information:

Sales Destination: Belgium, France, all European Union and UK

For and on behalf of
TUV Rheinland/CCIC (Fujian) Co.,Ltd. Xiamen Branch

Rick Li

2024-06-27 Rick Li / Project Engineer
Date Name/Position

Sample information is provided by customer. Test result is drawn according to the kind and extent of tests performed. This test report relates to the above mentioned test sample. Without permission of the test center this test report is not permitted to be duplicated in extracts. This test report does not entitle to carry any safety mark on this or similar products.

"Decision Rule" document announced in our website (<https://www.tuv.com/landingpage/en/qm-gcn/>) describes the statement of conformity and its rule of enforcement for test results are applicable throughout this test report.

Test Report No.: **168481325a 001**

Page 2 of 18

Material list

Material No.	Material	Color	Location
M001	Plastic, ABS	Beige	Inner plastic of lid
M002	Metal	Silvery	Filter
M003	Silicone	Translucent	Seal ring
M004	Glass	Transparent	Body
M005	Whole product	Multicolor	Bottle with lid and filter

Overall Results:

Test No.	Tested item:	Conclusion
1	Sensorial examination	Pass
2	Global Migration	Pass
3	Global Migration from Silicone	Pass
4	Specific Migration of Metals	Pass
5	Colourfastness	Pass
6	Specific Migration of Primary Aromatic Amines	Pass
7	Specific Release of Metals	Pass
8	Specific Migration of Butadiene	Pass
9	Specific Migration of Acrylonitrile	Pass
10	Total Butadiene	Pass
11	Release of Lead and Cadmium from Glassware	Pass

Result

1. Sensorial examination

Test method: It is examined to the extent of food simulant being used, which comes into contact with the product, undergoes detectable changes in taste and smell.

For this purpose, the food simulant was stored in the product under the below mentioned time and temperature. Afterwards, the food simulant was examined by an appropriate number of tasters with regard to any divergence in smell and taste. Another test sample, which was used as a reference, was treated by the same way except that it had no contact with the product to be tested.

Before testing, the product had been cleaned according to the product's instruction manual or in the absence of such manual, by normal household cleaning.

Evaluation scheme: The test is carried out on the basis of ISO 13302 by paired comparison test:

- 0 = No perceptible difference
- 1 = Just perceptible difference (still difficult to define)
- 2 = Slight difference (possible to define)
- 3 = Marked difference
- 4 = Strong difference
- Limit: 3 (failed)

The following food simulants and conditions were applied:

Food simulant	Test duration / Temperature
Water	24 hour(s) / 40 °C

Test No.:	T001
Material No.:	M005
Parameter:	Result
Transfer of Smell:	0
Transfer of Taste:	0

Test Report No.: **168481325a 001**

Page 4 of 18

2. Global Migration

Test method: The migratory behaviour is examined with reference to Commission Regulation 10/2011 and its amendments.

Limit: Commission Regulation (EU) No 10/2011 and its amendments

The following food simulants and conditions were applied:

Food simulant	Test duration / Temperature
Acetic acid 3 %	2 hour(s) / 70 °C
Ethanol 50 %	2 hour(s) / 70 °C

Test No.:	T001					
Material No.:	M001					
Migration ratio:	167 ml / dm ²					
Parameter	Unit	RL	1 st Migration Result	2 nd Migration Result	3 rd Migration Result	Limit
Acetic acid 3 %	mg/dm ²	2	3	3	2	10
Ethanol 50 %	mg/dm ²	2	3	2	<RL	10

Abbreviations:

RL = Reporting Limit

mg/dm² = Milligram per square decimetre

ml/dm² = Mililitre per square decimetre

< = Less than

Test Report No.: **168481325a 001**

Page 5 of 18

3. Global Migration from Silicone

Test method: The migratory behaviour is examined with reference to Chapter V, Article 18 of Commission regulation 10/2011 and its amendments. Deviating to the regulations the following tests were performed as orientating single tests.

Limit: Resolution AP (2004) 5 on silicones used for food contact applications

The following food simulants and conditions were applied:

Food simulant	Test duration / Temperature
Acetic acid 3 %	2 hour(s) / 70 °C
Ethanol 50 %	2 hour(s) / 70 °C

Test No.:	T001		
Material No.:	M003		
Parameter	Unit	Result	Limit
Acetic acid 3 %	mg/dm ²	< 2	10
Ethanol 50 %	mg/dm ²	< 2	10

Abbreviations:

mg/dm² = Milligram per square decimetre

< = Less than

Test Report No.: **168481325a 001**

Page 6 of 18

4. Specific Migration of Metals

Test method: The migratory behaviour was examined with reference to Commission Regulation (EU) No. 10/2011 and its amendments. Determination by ICP-MS.

Limit: Commission Regulation (EU) No 10/2011 and its amendments

The following food simulant and condition was applied:

Food simulant	Test duration / Temperature
Acetic acid 3 %	24 hour(s) / 40 °C

Test No.:	T001					
Material No.:	M001					
Migration ratio:	167 ml / dm ²					
Parameter	Unit	RL	1 st Migration Result	2 nd Migration Result	3 rd Migration Result	Limit
Aluminium	mg/kg	0.1	n.d.	n.d.	n.d.	1
Antimony	mg/kg	0.01	n.d.	n.d.	n.d.	0.04
Arsenic	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.
Barium	mg/kg	0.1	n.d.	n.d.	n.d.	1
Cadmium	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
Total Chromium	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.
Cobalt	mg/kg	0.01	n.d.	n.d.	n.d.	0.05
Copper	mg/kg	0.5	n.d.	n.d.	n.d.	5
Iron	mg/kg	5	n.d.	n.d.	n.d.	48
Lead	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.
Lithium	mg/kg	0.1	n.d.	n.d.	n.d.	0.6
Manganese	mg/kg	0.1	n.d.	n.d.	n.d.	0.6
Mercury	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.
Nickel	mg/kg	0.01	n.d.	n.d.	n.d.	0.02
Zinc	mg/kg	1	n.d.	n.d.	n.d.	5
Europium	mg/kg	0.01	n.d.	n.d.	n.d.	--
Gadolinium	mg/kg	0.01	n.d.	n.d.	n.d.	--
Lanthanum	mg/kg	0.01	n.d.	n.d.	n.d.	--
Terbium	mg/kg	0.01	n.d.	n.d.	n.d.	--
Sum of Lanthanide substances	mg/kg	0.01	n.d.	n.d.	n.d.	0.05

Test Report No.: **168481325a 001**

Page 7 of 18

Abbreviations:

- RL = Reporting limit
- n.d. = Not detected
- mg/kg = Milligram per kilogram
- ml/dm² = Millilitre per square decimetre
- < = Less than

Remark:

Single component with an amount below reporting limit was not considered by the calculation of the sum. In the case of all lanthanide substances europium, gadolinium, lanthanum and terbium were not detected, the result is stated n.d.

Test Report No.: **168481325a 001**

Page 8 of 18

5. Colourfastness

Test method: 24th Communication on the testing of plastics in Bundesgesundheitsbl. 15 (1972) 285

Requirement: BfR Recommendations on Food Contact Materials (formerly "Plastics Recommendations") Part IX "Colorants for Plastics and other Polymers used in Commodities" - *No transfer of colorants to foodstuffs is permitted*

Test No.:	T001
Material No.:	M001
Parameter – Colourfastness to	Difference between blank and filter paper contacted with sample
Water	No
Acetic acid 3 %	No
Ethanol 50 %	No
Oil	No

Test Report No.: **168481325a 001**

Page 9 of 18

6. Specific Migration of Primary Aromatic Amines

Test method: The migratory behaviour was examined with reference to Commission Regulation 10/2011 and its amendments. Determination by LC-MS/MS.

Limit: Commission Regulation (EU) No 10/2011 and its amendments

The following food simulant and condition were applied:

Food simulant	Test duration / Temperature
Acetic acid 3 %	24 hour(s) / 40 °C

Test No.:		T001					
Material No.:		M001					
Migration ratio:		167 ml / dm ²					
Parameter	CAS no.	Unit	RL	1 st Migration Result	2 nd Migration Result	3 rd Migration Result	Limit
2,4-Diaminoanisole	615-05-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
2,4-toluediamine	95-80-7	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-oxydianiline	101-80-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
Benzidine	92-87-5	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-methylenedianiline	101-77-9	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
o-anisidine	90-04-0	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
o-Toluidine	95-53-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-bi-o-toluidine	119-93-7	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
3,3'-Dimethoxybenzidine	119-90-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4-chloroaniline	106-47-8	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
p-cresidine	120-71-8	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4-chloro-o-toluidine	95-69-2	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4-aminobiphenyl	92-67-1	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-Methylene-di-o-toluidine	838-88-0	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-thiodianiline	139-65-1	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
2-Naphthylamine	91-59-8	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
3,3'-Dichlorobenzidine	91-94-1	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4,4'-methylene-bis-(2-chloro-aniline)	101-14-4	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
4-aminoazobenzene	60-09-3	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
o-aminoazotoluene	97-56-3	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
2,4,5-Trimethylaniline	137-17-7	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
2-Methyl-5-nitroaniline	99-55-8	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
m-phenylenediamine	108-45-2	mg/kg	0.002	n.d.	n.d.	n.d.	n.d.
Benzoguanamine	91-76-9	mg/kg	0.01	n.d.	n.d.	n.d.	5
4,4'-Methylenebis-(3-chloro-2,6-diethylaniline)	106246-33-7	mg/kg	0.01	n.d.	n.d.	n.d.	0.05

PAA's not listed in entry 43 to Appendix 8 of Annex XVII to Regulation (EC) No 1907/2006 and its amendments

Test Report No.: **168481325a 001**

Page 10 of 18

p-toluidine	106-49-0	mg/kg	0.01	n.d.	n.d.	n.d.	-
p-phenylenediamine	106-50-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Methyl-4-nitroaniline	99-52-5	mg/kg	0.01	n.d.	n.d.	n.d.	-
o-phenylenediamine	95-54-5	mg/kg	0.01	n.d.	n.d.	n.d.	-
1,5-naphthylenediamine	2243-62-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
Aniline	62-53-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,4-Dimethylaniline	95-68-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,6-Dimethylaniline	87-62-7	mg/kg	0.01	n.d.	n.d.	n.d.	-
5-Chloro-2-methylaniline	95-79-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,6-toluenediamine	823-40-5	mg/kg	0.01	n.d.	n.d.	n.d.	-
5-Amino-6-methyl-1,3-dihydro-2H-benzimidazol-2-one	67014-36-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-aminobenzamide	2835-68-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
3-Amino-4-methylbenzamide	19406-86-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
m-Anisidine	536-90-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
m-toluidine	108-44-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-Ethoxyaniline	156-43-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-ethoxyaniline	94-70-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-Chloro-3-methoxyaniline	13726-14-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
1,3-Diiminoisindoline	3468-11-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
3-Amino-4-methoxybenzanilide	120-35-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,4,5-Trichloroaniline	636-30-6	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-chloro-2,5-dimethoxyaniline	6358-64-1	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Methoxy-4-nitroaniline	97-52-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
5-Chloro-2-methoxyaniline	95-03-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
3-Chloroaniline	108-42-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Chloroaniline	95-51-2	mg/kg	0.01	n.d.	n.d.	n.d.	-
Dimethyl-2-aminoterephthalate	5372-81-6	mg/kg	0.01	n.d.	n.d.	n.d.	-
Biphenyl-2-ylamine	90-41-5	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,5-Dichloroaniline	95-82-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Nitroaniline	88-74-4	mg/kg	0.01	n.d.	n.d.	n.d.	-
4-Aminotoluene-3-sulfonic acid	88-44-8	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Aminonaphthalene-1-sulfonic acid	81-16-3	mg/kg	0.01	n.d.	n.d.	n.d.	-
2,4-Dinitroaniline	97-02-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
2-Chloro-4-nitroaniline	121-87-9	mg/kg	0.01	n.d.	n.d.	n.d.	-
Sum of Primary Aromatic Amines	-	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.

Test Report No.: **168481325a 001**

Page 11 of 18

Abbreviations:

- RL = Reporting Limit
- n.d. = Not detected
- mg/kg = Milligram per kilogramm
- ml/dm² = Millilitre per square decimetre
- < = Less than

Remark:

- *1 Sum of Primary Aromatic Amines does not include the value of Benzoguanamine and 4,4'-Methylenebis-(3-chloro-2,6-diethylaniline) as the SML of both substances should refer to EU 10/2011 Union list.
Single components with an amount of less than reporting limit were not considered by the calculation of the sum. In the case of all of Primary Aromatic Amines were not detected, the result is stated n.d.

Test Report No.: **168481325a 001**

Page 12 of 18

7. Specific Release of Metals

Test method: The sample preparation is performed with reference to "Technical Guide on Metals and alloys used in food contact materials". The migratory behaviour is examined with reference to Chapter V, Article 18 of Commission regulation 10/2011 and its amendments. Presence of elements were detected by means of ICP-MS.

Limit: Technical Guide on Metals and alloys used in food contact materials

The following food simulant and condition was applied:

Food simulant	Test duration / Temperature
Citric Acid 0.5 %	24 hour(s) / 40 °C

Test No.:	T001					
Sample No.:	M002					
Volume to surface area ratio	250 ml / dm ²					
			Sum 1 st + 2 nd test		3 rd test	
Parameter	Unit	RL	Result	Limits ^(*)	Result	Limits ^(*)
Silver (Ag)	mg/kg	0.05	<RL	0.56	<RL	0.08
Aluminum (Al)	mg/kg	0.1	<RL	35	<RL	5
Cobalt (Co)	mg/kg	0.01	<RL	0.14	<RL	0.02
Chromium (Cr)	mg/kg	0.01	0.05	1.75	<RL	0.25
Copper (Cu)	mg/kg	0.5	<RL	28	<RL	4
Iron (Fe)	mg/kg	5	<RL	280	<RL	40
Manganese (Mn)	mg/kg	0.1	<RL	12.6	<RL	1.8
Molybdenum (Mo)	mg/kg	0.02	<RL	0.84	<RL	0.12
Nickel (Ni)	mg/kg	0.01	0.02	0.98	<RL	0.14
Tin (Sn)	mg/kg	10	<RL	700	<RL	100
Vanadium (V)	mg/kg	0.01	<RL	0.07	<RL	0.01
Zinc (Zn)	mg/kg	1	<RL	35	<RL	5
Arsenic (As)	mg/kg	0.002	<RL	0.014	<RL	0.002
Barium (Ba)	mg/kg	0.1	<RL	8.4	<RL	1.2
Beryllium (Be)	mg/kg	0.01	<RL	0.07	<RL	0.01
Cadmium (Cd)	mg/kg	0.002	<RL	0.035	<RL	0.005
Mercury (Hg)	mg/kg	0.003	<RL	0.021	<RL	0.003
Lithium (Li)	mg/kg	0.02	<RL	0.336	<RL	0.048
Lead (Pb)	mg/kg	0.01	<RL	0.07	<RL	0.01
Antimony (Sb)	mg/kg	0.01	<RL	0.28	<RL	0.04
Thallium (Tl)	mg/kg	0.0001	<RL	0.0007	<RL	0.0001

Test Report No.: **168481325a 001**

Page 13 of 18

Abbreviations:

- RL = Reporting Limit
- mg/kg = Milligram per kilogram
- < = Less than

Remark:

- *1 Compliance is established on the findings on the third test for products intended for repeated use.
- *2 In addition, the sum of each metal in the first and second test should not exceed the sevenfold limit.

Test Report No.: **168481325a 001**

Page 14 of 18

8. Specific Migration of Butadiene

Test method: The migratory behavior was examined with reference to Commission Regulation (EU) No. 10/2011 and its amendments. Determination with ref. to CEN/TS 13130-15:2005.

Limit: With reference to Commission Regulation (EU) No 10/2011 and its amendments

The following food simulant and condition were applied:

Food simulant	Test duration / Temperature
Ethanol 50 %	24 hour(s) / 40 °C

Test No.:	T001						
Sample No.:	M001						
Migration ratio:	167 ml / dm ²						
Parameter	CAS No.	Unit	RL	1 st Migration Result	2 nd Migration Result	3 rd Migration Result	Limit
Butadiene	106-99-0	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.

Food simulant	Test duration / Temperature
Acetic acid 3 %	24 hour(s) / 40 °C

Test No.:	T001						
Sample No.:	M001						
Migration ratio:	167 ml / dm ²						
Parameter	CAS No.	Unit	RL	1 st Migration Result	2 nd Migration Result	3 rd Migration Result	Limit
Butadiene	106-99-0	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.

Abbreviations:

RL = Reporting Limit

n.d. = Not detected

mg/kg = Milligram per kilogram

ml/dm² = Mililitre per square decimetre

< = Less than

Test Report No.: **168481325a 001**

Page 15 of 18

9. Specific Migration of Acrylonitrile

Test method: The migratory behavior was examined with reference to Commission Regulation (EU) No. 10/2011 and its amendments. Determination with ref. to EN 13130-3:2004.

Limit: With reference to Commission Regulation (EU) No 10/2011 and its amendments

The following food simulant and condition were applied:

Food simulant	Test duration / Temperature
Acetic acid 3 %	24 hour(s) / 40 °C

Test No.:	T001						
Sample No.:	M001						
Migration ratio:	167 ml / dm ²						
Parameter	CAS No.	Unit	RL	1 st Migration Result	2 nd Migration Result	3 rd Migration Result	Limit
Acrylonitrile	107-13-1	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.

Food simulant	Test duration / Temperature
Ethanol 50 %	24 hour(s) / 40 °C

Test No.:	T001						
Sample No.:	M001						
Migration ratio:	167 ml / dm ²						
Parameter	CAS No.	Unit	RL	1 st Migration Result	2 nd Migration Result	3 rd Migration Result	Limit
Acrylonitrile	107-13-1	mg/kg	0.01	n.d.	n.d.	n.d.	n.d.

Abbreviations:

RL = Reporting Limit

n.d. = Not detected

mg/kg = Milligram per kilogram

ml/dm² = Mililitre per square decimetre

< = Less than

Test Report No.: **168481325a 001**

Page 16 of 18

10. Total Butadiene

Test method: Determination of Butadiene total content in plastic material acc. to DIN 13130-4

Limit: Commission Regulation (EU) No 10/2011 and its amendments

Test No.:	T001			
Sample No.:	M001			
Parameter	Unit	RL	Result	Limit
Butadiene	mg/kg	0.1	0.7	1

Abbreviations:

RL =Reporting limit

mg/kg = Milligram per kilogram

< = Less than

Test Report No.: **168481325a 001**

Page 17 of 18

11. Release of Lead and Cadmium from Glassware

Test method: The test is performed reference to EN 1388-1:1995, EN 1388-2:1995 and DIN 51031:1986 respectively. The concentration of the elements is examined by means of atomic absorption spectroscopy or ICP-MS.

Limit: Directive 84/500/EEC and its amendments / BS 6748:1986 + A1:2011

The following food simulant and condition was applied:

Food simulant	Test duration / Temperature
Acetic acid 4 %	24 hours / 22 °C

Test No.:	T001		
Category:	2		
Sample No.:	M004		
Parameter	Unit	Result	Limit (*1)
Lead (Pb)	mg/l	< 0.2	4.0
Cadmium (Cd)	mg/l	< 0.02	0.3

Abbreviations:

mg/dm² = Milligram per square decimetre

mg/l = Milligram per litre


< = Less than

Remarks:

*1 According to EU Directive 84/500/EEC and BS 6748:1986, articles in contact with food should not exceed the following limits

Category	Description	Lead	Cadmium
1	Articles which can't and articles which can be filled, the internal depth of which, measured from the lowest point to the horizontal plane passing through the upper rim, does not exceed 25 mm	0.8 mg/dm ²	0.07 mg/dm ²
2	Other articles which can be filled	4.0 mg/l	0.3 mg/l
3	Cooking ware; packaging and storage vessels having a capacity of more than three litres	1.5 mg/l	0.1 mg/l


Sample Photos:



M001




M002




M003



M004



M005



Product

- END -

